

SPESIFICATION GREASE PROOF PAPER 40 GSM

PHYSICAL TEST	UNIT	STANDART
Gsm	gr / m ²	37 - 43
Thickness	micron	55 - 70
Roughness Top Bottom	ml/min	350 max 400 max
Cobb test	gr/m ²	35 max
Moisture	%	8,0 max
Klt Number		7 min

Test Condition :

Temperatur 23 ± 1(°C)
Relative Humidity 50 ± 2 (%)

COUNTRY OF ORIGIN: INDONESIA



Faint text, possibly a company name or address, located below the logo.

SPECIFICATION GREASE PROOF PAPER 50 GSM

PHYSICAL TEST	UNIT	STANDART
Gsm	gr / m ²	50 ± 5%
Thickness	micron	55 – 75
Roughness Top Bottom	ml/ min	350 max 400 max
Cobb test	gr/m ²	35 max
Moisture	%	8,0 max
Kit Number		7 min

Test Condition :

Temperature 23 ± 1(°C)
Relative Humidity 50 ± 2 (%)

